



ELGAMATIC NEO 100

Solid wire Gas Metal
Arc Solid Wires

Classifications

EN ISO 14341-A G 42 4 M21 3Si1 G 38 3 C1 3Si1
AWS A5.18 ER70S-6

ELGAMATIC NEO 100 is a premium bronze-coated, manganese-silicon, G3Si1 type mild steel wire engineered for superior welding performance with CO₂ or Ar/CO₂ shielding gases. Its advanced bronze coating ensures exceptional arc stability, smooth bead appearance, and consistent quality, even under demanding conditions.

Designed for high-speed robotic and mechanized welding, ELGAMATIC NEO 100 delivers unmatched reliability at very high amperages, making it the ideal choice for automated production lines.

Thanks to its precisely controlled metallurgy, it offers consistent mechanical properties and toughness at -40°C.

Applications: Perfect for structural steel fabrication, transportation, heavy equipment manufacturing, agricultural machinery, and earth-moving applications—where productivity and quality matter most.

Shielding Gas M21, 80% Ar + 20% CO₂, 12-
C1, 100% CO₂, 12-18 l/min
Welding Current DC+

Weld metal chemistry %

	%C	%Si	%Mn	%P	%S	%Cr	%Ni	%Mo	%Cu
Min	0,06	0,70	1,40						
Typical	0,07	0,8	1.43	0,02	0,02	0,01	0,01	0,01	
Max	0,10	1,00	1,56	0,025	0,025	0,15	0,15	0,15	0,35

Notes :

Also available in AUTOPAC, a twist-free pay-off pack. For more information about Part no, type of spool and winding, please study the price list.

Mechanical properties

Welding Conditions : As Welded (M21)

Values	Min.	Typ.		T °C	Min.	Typ.
Yield Strength, Re	420	450	MPa	-40	47	60
Tensile Strength, Rm	500	560	MPa			
Elongation A5	22	26	%			

CE	TÜV	DB	LR	DNV	BV	ABS	RINA	UKCA
x	X	X		X				

Available diameters : 1.0 - 1.2mm

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and ITW Welding AB expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the corresponding EN ISO specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by ITW Welding AB.